

6180 Red



6159 Pink



6038 Terracotta




6146 Coral



6211 Gold



6559 Spring




6570 Mint Green



6557 Forest




6430 Blue




6445 Lagoon




6431 Teal




2404 London Light Blue




6758 Silver Gray




6347 Beige




3764 Taupe



6830 Black




6873 Anthracite






6375 Oak design



6381 Maple design



6350 Light Cherry Design

DESCRIPTION	Standard	Requirement	Units	Results
Dry-Tex System				
Ecofit System				
PRODUCT DESCRIPTION				
Surface treatment	-	-	-	Triple-Action Protecsol®
Surface complex	-	-	-	D-Max™/D-Max + TM
Foam	-	-	-	Double density CXP-HD™
Thickness	EN 428	-	mm	9
Weight	EN 430	-	kg/m ²	5,4
Length	EN 426	-	lm	22 Max
Width	EN 426	-	lm	1.5
SPORT PROPERTIES				
Shock absorption	EN 14808	≥25	%	P2
Vertical deformation	EN 14809	≤3.5	mm	≤3
Energy return	NF P 90 203	≥ 0.31	m/s	≥ 0.31
Sliding coefficient	EN 13036-4	80 to 110	-	80 - 110
Ball bounce	EN 12235	≥ 90	%	≥ 90
Ball speed	UEFA	50 to 65	cm	-
	ITF	-	-	-
TECHNICAL CHARACTERISTICS				
Abrasion resistance	EN ISO 5470-1	≤ 1000	mg	≤ 350
Impact resistance	EN 1517	≥ 8	N/m	≥ 8
Indentation resistance	EN 1516	≤ 0.5	mm	≤ 0.5
CLASSIFICATION				
Fire	EN 13501-1	-	-	Cfl-s1
Special treatment	-	-	-	Sanosol®
CE MARKING				
	EN 14 904 :2006	-	-	Fire Shock Absorption Sliding Coefficient Abrasion Resistance Resistance to roaling load